# SIMCHEM STARCH ADDITIVE PRODUCTS

# **Starch Philosophy**

A sticky, stringy starch rheology is the key to achieving a strong bond at high corrugator speeds. This is accomplished by using a proprietary pearl starch modifier (AirLock) added in the primary cook to break down the starch molecule, allowing our customers to cook more starch in the primary. No other performance-enhancing additives are needed.

#### Additive Products – SimChem Formula

#### The following products are used in every SimChem Batch.

AIRLOCK	ULTRASEAL RESIN
Ammonium-persulfate solution	Ketone-formaldehyde water-proofing resin.
Modifies pearl starch, allowing user to cook more	Insolubilizes starch glue line.
pearl in primary cook. (135-145 lbs.)	High-quality raw materials reduce usage and increase
Gives starch sticky, stringy rheology	performance.
<u>Product Benefits</u>	<u>Product Benefits</u>
• Faster corrugator speeds,	<ul> <li>Improved water resistance</li> </ul>
<ul> <li>Stronger and faster bond,</li> <li>Improved paper penetration</li> </ul>	<ul> <li>Consistently high wet pins</li> <li>Minimal usage per batch.</li> </ul>
<ul> <li>Improved paper penetration</li> <li>Improved Pin Test Results,</li> </ul>	<ul> <li>Up to 5% Increase in corrugator speed.</li> </ul>
• 17 lbs. per batch.	• 38 lbs. per batch.
Manufactured in Greenville, SC	<ul> <li>Manufactured in Greenville, SC.</li> </ul>
BXL – 50 LIQUID BORA	FRS – 10 DEFOAMER
<ul> <li>BXL – 50 LIQUID BORA</li> <li>Highly-concentrated, liquid borate solution to replace</li> </ul>	<ul> <li>FRS – 10 DEFOAMER</li> <li>Highly effective defoaming agent formulated for</li> </ul>
<ul> <li>Highly-concentrated, liquid borate solution to replace powdered borax.</li> </ul>	<ul> <li>Highly effective defoaming agent formulated for starch-based adhesives.</li> </ul>
<ul> <li>Highly-concentrated, liquid borate solution to replace powdered borax.</li> <li>Supplied in totes and pumped to batch via starch</li> </ul>	<ul> <li>Highly effective defoaming agent formulated for starch-based adhesives.</li> <li>Components satisfy <u>FDA 21 CFR Sec. 176.170</u>. (Indirect</li> </ul>
<ul> <li>Highly-concentrated, liquid borate solution to replace powdered borax.</li> <li>Supplied in totes and pumped to batch via starch system infrastructure.</li> </ul>	<ul> <li>Highly effective defoaming agent formulated for starch-based adhesives.</li> <li>Components satisfy <u>FDA 21 CFR Sec. 176.170</u>. (Indirect Food Contact)</li> </ul>
<ul> <li>Highly-concentrated, liquid borate solution to replace powdered borax.</li> <li>Supplied in totes and pumped to batch via starch system infrastructure.</li> <li><u>Product Benefits</u></li> </ul>	<ul> <li>Highly effective defoaming agent formulated for starch-based adhesives.</li> <li>Components satisfy <u>FDA 21 CFR Sec. 176.170</u>. (Indirect Food Contact)</li> <li>High activity level kills foam at low usage levels.</li> </ul>
<ul> <li>Highly-concentrated, liquid borate solution to replace powdered borax.</li> <li>Supplied in totes and pumped to batch via starch system infrastructure.</li> <li><u>Product Benefits</u> <ul> <li>Replaces hopper system</li> </ul> </li> </ul>	<ul> <li>Highly effective defoaming agent formulated for starch-based adhesives.</li> <li>Components satisfy <u>FDA 21 CFR Sec. 176.170</u>. (Indirect Food Contact)</li> <li>High activity level kills foam at low usage levels.</li> <li><u>Product Benefits</u></li> </ul>
<ul> <li>Highly-concentrated, liquid borate solution to replace powdered borax.</li> <li>Supplied in totes and pumped to batch via starch system infrastructure.</li> <li><u>Product Benefits</u> <ul> <li>Replaces hopper system</li> <li>Less dust and borax spills</li> </ul> </li> </ul>	<ul> <li>Highly effective defoaming agent formulated for starch-based adhesives.</li> <li>Components satisfy <u>FDA 21 CFR Sec. 176.170</u>. (Indirect Food Contact)</li> <li>High activity level kills foam at low usage levels.</li> <li><u>Product Benefits</u> <ul> <li>Highly efficient = low usage</li> </ul> </li> </ul>
<ul> <li>Highly-concentrated, liquid borate solution to replace powdered borax.</li> <li>Supplied in totes and pumped to batch via starch system infrastructure.</li> <li><u>Product Benefits</u> <ul> <li>Replaces hopper system</li> </ul> </li> </ul>	<ul> <li>Highly effective defoaming agent formulated for starch-based adhesives.</li> <li>Components satisfy <u>FDA 21 CFR Sec. 176.170</u>. (Indirect Food Contact)</li> <li>High activity level kills foam at low usage levels.</li> <li><u>Product Benefits</u> <ul> <li>Highly efficient = low usage</li> <li>Instantly effective</li> </ul> </li> </ul>
<ul> <li>Highly-concentrated, liquid borate solution to replace powdered borax.</li> <li>Supplied in totes and pumped to batch via starch system infrastructure.</li> <li><u>Product Benefits</u> <ul> <li>Replaces hopper system</li> <li>Less dust and borax spills</li> <li>Consistent mix throughout batch</li> </ul> </li> </ul>	<ul> <li>Highly effective defoaming agent formulated for starch-based adhesives.</li> <li>Components satisfy <u>FDA 21 CFR Sec. 176.170</u>. (Indirect Food Contact)</li> <li>High activity level kills foam at low usage levels.</li> <li><u>Product Benefits</u> <ul> <li>Highly efficient = low usage</li> <li>Instantly effective</li> <li>Low environmental impact.</li> </ul> </li> </ul>
<ul> <li>Highly-concentrated, liquid borate solution to replace powdered borax.</li> <li>Supplied in totes and pumped to batch via starch system infrastructure.</li> <li><u>Product Benefits</u> <ul> <li>Replaces hopper system</li> <li>Less dust and borax spills</li> <li>Consistent mix throughout batch</li> <li>Prevents "fish-eyes" in starch.</li> </ul> </li> </ul>	<ul> <li>Highly effective defoaming agent formulated for starch-based adhesives.</li> <li>Components satisfy <u>FDA 21 CFR Sec. 176.170</u>. (Indirect Food Contact)</li> <li>High activity level kills foam at low usage levels.</li> <li><u>Product Benefits</u> <ul> <li>Highly efficient = low usage</li> <li>Instantly effective</li> </ul> </li> </ul>

Ben Simmons (919) 593 – 4270





### **Other Starch Products**

# The following products are available for customers, but not required in SimChem's standard formula.

MACHNE CLEAN STARCH CLEANER	MAXXGOLD FORMALDEHYDE-FREE RESIN
Starch cleaning agent used to clean all corrugated	• High quality resin product made from sugar molecule.
equipment (storage tanks, starch lines)	<ul> <li>100% formaldehyde free – ZERO formaldehyde in</li> </ul>
• Dilute desired amount with water and pump through	product formula.
starch system.	Revived Pre-manufacturing Notice (PNA) under EPA's
• Spray on floor, tanks, and equipment.	Toxic Substance Control Act (TSCA) Approval Process
<u>Product Benefits</u> :     Characterile lines will a minute the second	(Lautenberg Chemical Safety Act of 2016)
<ul> <li>Cleans tanks, lines, rolls, equipment</li> <li>Non-hazardous – safe and easy to use.</li> </ul>	<ul> <li>Allows manufacturing and trials at no cost to customer to gather more data.</li> </ul>
<ul> <li>Non-hazardous – safe and easy to use.</li> <li>Non-foaming – can be agitated</li> </ul>	<ul> <li>Must follow strict handling and disposal</li> </ul>
<ul> <li>25% Solution – 2,375 lbs. : 625 lbs. + 1,750 lbs. water</li> </ul>	guidelines
for full system clean.	$\circ$ All data must be submitted to EPA.
• 25% Solution – 50 lbs.	<ul> <li>Supplied in corrugated totes for easy disposal – saves</li> </ul>
Manufactured in Pendergrass, GA	3 million lbs. of cleaning water per year.
AIRSEAL – SWIFT	ULTRABOND OBM
AIRSEAL – SWIFT     Performance-enhancing starch additive designed to	ULTRABOND OBM • One-bag starch mix formulated for Asitrade/Laminator
<ul> <li>Performance-enhancing starch additive designed to increase corrugator Runability and speed.</li> <li>Can be blended with ketone formaldehyde resin.</li> </ul>	<ul> <li>One-bag starch mix formulated for Asitrade/Laminator machines, or other small volume starch applications.</li> <li>20 – 25 sec. viscosity (Love Cup) and 142°F Gel Temp.</li> </ul>
<ul> <li>Performance-enhancing starch additive designed to increase corrugator Runability and speed.</li> <li>Can be blended with ketone formaldehyde resin. (50%/50%)</li> </ul>	<ul> <li>One-bag starch mix formulated for Asitrade/Laminator machines, or other small volume starch applications.</li> <li>20 – 25 sec. viscosity (Love Cup) and 142°F Gel Temp.</li> <li>No caustic or borax required – included in formulation.</li> </ul>
<ul> <li>Performance-enhancing starch additive designed to increase corrugator Runability and speed.</li> <li>Can be blended with ketone formaldehyde resin. (50%/50%)</li> <li><u>Product Benefits</u></li> </ul>	<ul> <li>One-bag starch mix formulated for Asitrade/Laminator machines, or other small volume starch applications.</li> <li>20 – 25 sec. viscosity (Love Cup) and 142°F Gel Temp.</li> <li>No caustic or borax required – included in formulation.</li> <li>Supplied in 50 lb. bags or 750 lb. Supersacks.</li> </ul>
<ul> <li>Performance-enhancing starch additive designed to increase corrugator Runability and speed.</li> <li>Can be blended with ketone formaldehyde resin. (50%/50%)</li> <li><u>Product Benefits</u> <ul> <li>Strong thermoset/cross-linked starch bond</li> </ul> </li> </ul>	<ul> <li>One-bag starch mix formulated for Asitrade/Laminator machines, or other small volume starch applications.</li> <li>20 – 25 sec. viscosity (Love Cup) and 142°F Gel Temp.</li> <li>No caustic or borax required – included in formulation.</li> <li>Supplied in 50 lb. bags or 750 lb. Supersacks.</li> <li><u>Product Benefits</u></li> </ul>
<ul> <li>Performance-enhancing starch additive designed to increase corrugator Runability and speed.</li> <li>Can be blended with ketone formaldehyde resin. (50%/50%)</li> <li><u>Product Benefits</u> <ul> <li>Strong thermoset/cross-linked starch bond</li> <li>Increased corrugator speeds when running</li> </ul> </li> </ul>	<ul> <li>One-bag starch mix formulated for Asitrade/Laminator machines, or other small volume starch applications.</li> <li>20 – 25 sec. viscosity (Love Cup) and 142°F Gel Temp.</li> <li>No caustic or borax required – included in formulation.</li> <li>Supplied in 50 lb. bags or 750 lb. Supersacks.</li> <li><u>Product Benefits</u> <ul> <li>Provides strong starch bond.</li> </ul> </li> </ul>
<ul> <li>Performance-enhancing starch additive designed to increase corrugator Runability and speed.</li> <li>Can be blended with ketone formaldehyde resin. (50%/50%)</li> <li><u>Product Benefits</u> <ul> <li>Strong thermoset/cross-linked starch bond</li> <li>Increased corrugator speeds when running heavy weight board.</li> </ul> </li> </ul>	<ul> <li>One-bag starch mix formulated for Asitrade/Laminator machines, or other small volume starch applications.</li> <li>20 – 25 sec. viscosity (Love Cup) and 142°F Gel Temp.</li> <li>No caustic or borax required – included in formulation.</li> <li>Supplied in 50 lb. bags or 750 lb. Supersacks.</li> <li><u>Product Benefits</u> <ul> <li>Provides strong starch bond.</li> <li>Easy to use – Requires mixing only</li> </ul> </li> </ul>
<ul> <li>Performance-enhancing starch additive designed to increase corrugator Runability and speed.</li> <li>Can be blended with ketone formaldehyde resin. (50%/50%)</li> <li><u>Product Benefits</u> <ul> <li>Strong thermoset/cross-linked starch bond</li> <li>Increased corrugator speeds when running heavy weight board.</li> <li>Increased water resistance</li> </ul> </li> </ul>	<ul> <li>One-bag starch mix formulated for Asitrade/Laminator machines, or other small volume starch applications.</li> <li>20 – 25 sec. viscosity (Love Cup) and 142°F Gel Temp.</li> <li>No caustic or borax required – included in formulation.</li> <li>Supplied in 50 lb. bags or 750 lb. Supersacks.</li> <li>Product Benefits         <ul> <li>Provides strong starch bond.</li> <li>Easy to use – Requires mixing only</li> <li>Increased machine speeds</li> </ul> </li> </ul>
<ul> <li>Performance-enhancing starch additive designed to increase corrugator Runability and speed.</li> <li>Can be blended with ketone formaldehyde resin. (50%/50%)</li> <li><u>Product Benefits</u> <ul> <li>Strong thermoset/cross-linked starch bond</li> <li>Increased corrugator speeds when running heavy weight board.</li> <li>Increased water resistance</li> <li>Non-hazardous, safe for plant personnel.</li> </ul> </li> </ul>	<ul> <li>One-bag starch mix formulated for Asitrade/Laminator machines, or other small volume starch applications.</li> <li>20 – 25 sec. viscosity (Love Cup) and 142°F Gel Temp.</li> <li>No caustic or borax required – included in formulation.</li> <li>Supplied in 50 lb. bags or 750 lb. Supersacks.</li> <li><u>Product Benefits</u> <ul> <li>Provides strong starch bond.</li> <li>Easy to use – Requires mixing only</li> <li>Increased machine speeds</li> </ul> </li> <li><u>300 gallon batch</u>: 15 – 18 bags per batch (750 lbs.) +</li> </ul>
<ul> <li>Performance-enhancing starch additive designed to increase corrugator Runability and speed.</li> <li>Can be blended with ketone formaldehyde resin. (50%/50%)</li> <li><u>Product Benefits</u> <ul> <li>Strong thermoset/cross-linked starch bond</li> <li>Increased corrugator speeds when running heavy weight board.</li> <li>Increased water resistance</li> </ul> </li> </ul>	<ul> <li>One-bag starch mix formulated for Asitrade/Laminator machines, or other small volume starch applications.</li> <li>20 – 25 sec. viscosity (Love Cup) and 142°F Gel Temp.</li> <li>No caustic or borax required – included in formulation.</li> <li>Supplied in 50 lb. bags or 750 lb. Supersacks.</li> <li>Product Benefits         <ul> <li>Provides strong starch bond.</li> <li>Easy to use – Requires mixing only</li> <li>Increased machine speeds</li> </ul> </li> </ul>

# **Developmental Products**

#### The following products are currently under development and available for trials.

ULTRABOND – K	CBB – 49
<ul> <li>Powdered mixture to replace pearl starch usage</li> <li>Starch-based Ingredients that simulates primary cook.</li> <li>Replaces up to 250 lbs. of plant Peral starch per batch, Replaces caustic and borax.</li> <li>No change to overall starch concertation – 28%.</li> <li>DRAWBACK – product still based on pearl starch.</li> <li>Supplied in 50 lbs. bags or Super Sack</li> <li>300 gal. Formula – 12-15 mins. mix time.         <ul> <li>150 lbs. – UltraBond – K (3 bags)</li> <li>750 lbs. – Plant Pearl Starch</li> <li>2,250 lbs. – Water</li> </ul> </li> </ul>	